

**verope**®

rely on



Mobile Crane



Crawler Crane



Tower Crane



Luffing Crane



Foundation Equipment



Truck Crane

# Construction Industry



# Construction Industry applications

The construction industry has never been more complex, building projects constantly increase. This means the requirements for the cranes and ropes used are also on the rise. verope offers various ropes, rope end fittings and customer-specific special solutions tailored to the construction industry.

verope provides a global retailer network for special wire ropes to serve the customers wherever the products are needed.

## **verope offers the following services:**


- Technical customer service
- Technical advice
- Rope inspections
- Theoretical rope service life calculation
- A broad range of rope tests such as
  - Tensile test up to 2500 kN
  - Bending fatigue test for various rope diameters
  - Various tests to determine the rotational behavior of ropes
  - Elongation measurement
  - Modulus of elasticity determination
  - Test to measure the rope flexibility
  - Diameter reduction under load measurement
  - Lateral stiffness determination

# Standard rope end connections



We are able to offer customized ropes with the correct endtermination for crane brands such as:


- Liebherr
- Terex
- Sennebogen
- Tadano Faun
- Manitowoc
- and much more




Flemish eye ferrule-secured termination



Ferrule-secured open thimble termination



Open spelter socket: Metal or resin socketing




Ferrule-secured eye termination



End stop: either metal-/resin socketing or swaged



Closed end socket: Metal or cast synthetic resin




Ferrule-secured thimble termination



Threaded socket swaged



Open socket swaged



Ferrule-secured solid thimble termination



Closed socket swaged

verope can also offer customer-specific solutions in addition to the standard rope end connections.  
Special solutions on request.

---


# Rope applications for Construction Industry



Mobile Crane



Crawler Crane



Tower Crane



Luffing Crane




Foundation Equipment




Truck Crane

# Mobile Crane / Telescopic Crane



© verope




## verotop

- very flexible
- rotation-resistant
- compacted strands

## Hoist Rope


## Auxillary Hoist Rope



## veropro 8 RS

- rotary swaged, 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer

## Luffing Rope




## verotop S

- very flexible
- rotation-resistant
- compacted strands
- very high breaking strength

## Hoist Rope


## Auxillary Hoist Rope



## veropower 8<sup>2</sup>

- rotary swaged, 8-strand
- non-rotation resistant
- parallel lay construction
- compacted outer strands
- rope core covered with a plastic layer


## Luffing Rope



## veropro 8

- 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer

## Luffing Rope




## veropro 10<sup>1</sup>

- 10-strand, very flexible
- non-rotation resistant
- compacted strands
- rope core covered with a plastic layer


## Luffing Rope

<sup>1</sup> Only available from 30 mm diameter | <sup>2</sup> For special applications

# Crawler Crane




© verope



**verotop**

- very flexible
- rotation-resistant
- compacted strands


Hoist Rope
Auxillary Hoist Rope



**veropro 8 RS**

- rotary swaged, 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer


Luffing Rope
Boom Hoist Rope
Pendant Rope



**verotop S**

- very flexible
- rotation-resistant
- compacted strands
- very high breaking strength


Hoist Rope
Auxillary Hoist Rope



**veropower 8<sup>2</sup>**

- rotary swaged, 8-strand
- non-rotation resistant
- parallel lay construction
- compacted outer strands
- rope core covered with a plastic layer


Luffing Rope
Boom Hoist Rope
Pendant Rope



**veropro 8**

- 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer

Luffing Rope
Boom Hoist Rope
Pendant Rope





**veropro 10<sup>1</sup>**

- 10-strand, very flexible
- non-rotation resistant
- compacted strands
- rope core covered with a plastic layer

Luffing Rope
Boom Hoist Rope
Pendant Rope

<sup>1</sup> Only available from 30 mm diameter | <sup>2</sup> For special applications


# Tower Crane



**verotop**

- very flexible
- rotation-resistant
- compacted strands

**Hoist Rope**




**verostar 8**

- 8-strand
- non-rotation resistant
- conventional strands
- rope core covered with a plastic layer

**Trolley Rope**


**Pendant Rope**



**verotop E**

- flexible
- rotation-resistant
- compacted strands

**Hoist Rope**




**veropro 8**

- 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer

**Trolley Rope**

**Pendant Rope**




**veropower 8**


- rotary swaged, 8-strand
- non-rotation resistant
- parallel lay construction
- compacted outer strands
- rope core covered with a plastic layer

**Pendant Rope**

# Luffing Crane




Note: In case pendant ropes are used on your crane please find our rope recommendation below.



**verotop**

- very flexible
- rotation-resistant
- compacted strands

**Hoist Rope**




**veropro 8**

- 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer

**Pendant Rope**


**Luffing Rope**



**verotop E**

- flexible
- rotation-resistant
- compacted strands

**Hoist Rope**




**veropro 8 RS**

- rotary swaged, 8-strand
- non-rotation resistant
- parallel lay construction
- compacted outer strands
- rope core covered with a plastic layer

**Pendant Rope**


**Luffing Rope**



**verostar 8**

- 8-strand
- non-rotation resistant
- conventional strands
- rope core covered with a plastic layer

**Pendant Rope**



**veropower 8<sup>1</sup>**


- 10-strand, very flexible
- non-rotation resistant
- compacted strands
- rope core covered with a plastic layer

**Pendant Rope**



**Luffing Rope**

<sup>1</sup> For special applications

# Foundation Equipment



## Hydraulic Grab




### verotop P

- rotation-resistant
- compacted strands
- rope core covered with a plastic layer

### Hoist Rope


### Auxiliary Hoist Rope



### verostar 8

- 8-strand
- non-rotation resistant
- conventional strands
- rope core covered with a plastic layer

### Feed Unit Rope




### verotop

- very flexible
- rotation-resistant
- compacted strands

### Hoist Rope


### Auxiliary Hoist Rope



### veropro 8

- 8-strand
- non-rotation resistant
- compacted outer strands
- rope core covered with a plastic layer

### Feed Unit Rope




### veropower 8


- rotary swaged, 8-strand
- non-rotation resistant
- parallel lay construction
- compacted outer strands
- rope core covered with a plastic layer

### Feed Unit Rope

# Truck Crane




© verope



## verotop

- very flexible
- rotation-resistant
- compacted strands

## Hoist Rope



## verotop E


- flexible
- rotation-resistant
- compacted strands

## Hoist Rope




---


# Special wire ropes for applications in **Construction Industry**




verotop P




verotop




verotop S




verotop E




verostar 8




veropro 8



veropro 8RS



veropower 8



veropro 10

# verotop P


Provides a very stable rope structure  
and achieves excellent bending fatigue  
results.

Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
16	5/8	1.248	241.7	24.6	252.7	25.7
17		1.408	272.8	27.8	285.3	29.1
18		1.579	305.8	31.2	319.8	32.6
19	3/4	1.759	340.8	34.7	356.3	36.3
20		1.949	377.6	38.5	394.8	40.2
21		2.149	416.3	42.4	435.3	44.4
22		2.359	456.9	46.6	477.7	48.7
22.4		2.445	473.6	48.3	495.3	50.5
23		2.578	499.3	50.9	522.2	53.2
24		2.807	543.7	55.4	568.6	57.9
25		3.046	590.0	60.1	616.9	62.9
25.4	1	3.144	609.0	62.1	636.8	64.9
26		3.294	638.1	65	667.3	68
27		3.553	688.1	70.1	719.6	73.3
28		3.821	740.1	75.4	773.9	78.9
28.6	1-1/8	3.986	772.1	78.7	807.4	82.3
29		4.099	793.9	80.9	830.1	84.6
30		4.386	849.6	86.6	888.4	90.5
31		4.683	907.1	92.4	948.6	96.7
32	1-1/4	4.990	966.6	98.5	1011	103
33		5.307	1028	104.7	1075	109.5
34		5.634	1091	111.2	1141	116.3
35	1-3/8	5.970	1156	117.8	1209	123.2
36		6.316	1223	124.7	1279	130.4
38	1-1/2	7.037	1363	138.9	1425	145.2
40		7.797	1510	153.9	1579	160.9
42		8.597	1665	169.7	1741	177.4
43		9.011	1745	177.9	1825	186
44		9.435	1827	186.2	1911	194.7
45	1-3/4	9.869	1911	194.8	1999	203.7
46		10.312	1997	203.5	2089	212.8
48		11.228	2175	221.6	2274	231.7
50	2	12.183	2360	240.5	2468	251.5
52		13.178	2552	260.1	2669	272
54	2-1/8	14.211	2753	280.5	2878	293.3

\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.



Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs	
			Rope grade	
			1960	2160
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	
16	5/8	0.84	0.38	27.2    28.4
17		0.95	0.43	30.7    32.1
18		1.06	0.48	34.4    35.9
19	3/4	1.18	0.54	38.3    40.1
20		1.31	0.59	42.4    44.4
21		1.44	0.66	46.8    48.9
22		1.58	0.72	51.4    53.7
22.4		1.64	0.75	53.2    55.7
23		1.73	0.79	56.1    58.7
24		1.89	0.86	61.1    63.9
25		2.05	0.93	66.3    69.3
25.4	1	2.11	0.96	68.5    71.6
26		2.21	1	71.7    75
27		2.39	1.08	77.3    80.9
28		2.57	1.16	83.2    87
28.6	1-1/8	2.68	1.22	86.8    90.8
29		2.75	1.25	89.2    93.3
30		2.95	1.34	95.5    99.9
31		3.15	1.43	102    106.6
32	1-1/4	3.35	1.52	108.6    113.6
33		3.57	1.62	115.5    120.8
34		3.79	1.72	122.7    128.3
35	1-3/8	4.01	1.82	130    135.9
36		4.24	1.93	137.5    143.8
38	1-1/2	4.73	2.15	153.2    160.2
40		5.24	2.38	169.8    177.5
42		5.78	2.62	187.2    195.7
43		6.06	2.75	196.2    205.1
44		6.34	2.88	205.4    214.8
45	1-3/4	6.63	3.01	214.9    224.7
46		6.93	3.14	224.5    234.8
48		7.55	3.42	244.5    255.6
50	2	8.19	3.71	265.2    277.4
52		8.85	4.02	286.9    300
54	2-1/8	9.55	4.33	309.4    323.5

1) The values are indicative only. Authoritative figures remain the metric ones!



The rope is fully lubricated. The finish available as standard is galvanized, bright finish on request. • Average fill factor 0.730 • Ordinary or Lang Lay available • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309; RCN=23-3 • Further details: www.verope.com/en/RCN

# verotop

A superior balanced rope when resistance to rotation becomes most critical.

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
8	5/16	0.313	61.1	6.2	62.7	6.4
9		0.397	77.3	7.9	79.4	8.1
10		0.490	95.4	9.7	98.0	10
11	7/16	0.593	115.5	11.8	118.6	12.1
12		0.705	137.4	14	141.2	14.4
12.7	1/2	0.790	153.9	15.7	158.1	16.1
13		0.828	161.3	16.4	165.7	16.9
14		0.960	187.0	19.1	192.2	19.6
15		1.102	214.7	21.9	220.6	22.5
16	5/8	1.254	244.3	24.9	251.0	25.6
17		1.415	275.8	28.1	283.3	28.9
18		1.587	309.2	31.5	317.7	32.4
19	3/4	1.768	344.5	35.1	353.9	36.1
20		1.959	381.7	38.9	392.2	40
21		2.160	420.8	42.9	432.4	44.1
22		2.371	461.9	47.1	474.5	48.4
22.4		2.458	478.8	48.8	491.9	50.1
23		2.591	504.8	51.4	518.6	52.9
24		2.821	549.7	56	564.7	57.5
25		3.061	596.4	60.8	612.8	62.4
25.4	1	3.160	615.7	62.7	632.5	64.5
26		3.311	645.1	65.7	662.8	67.5
27		3.571	695.7	70.9	714.7	72.8
28		3.840	748.2	76.2	768.7	78.3
28.6	1-1/8	4.006	780.6	79.5	802.0	81.7
29		4.119	802.6	81.8	824.5	84
30		4.408	858.9	87.5	882.4	89.9
31		4.707	917.1	93.4	942.2	96
32	1-1/4	5.015	977.2	99.6	1004	102.3
33		5.334	1039	105.9	1068	108.8
34		5.662	1103	112.4	1133	115.5
35	1-3/8	6.000	1169	119.1	1201	122.4
36		6.348	1237	126	1271	129.5
38	1-1/2	7.072	1378	140.4	1416	144.3
40		7.837	1527	155.6	1569	159.8
41		8.233	1604	163.5	1648	167.9
42		8.640	1683	171.5	1729	176.2
43		9.056	1764	179.8	1813	184.7
44		9.482	1848	188.3	1898	193.4
45	1-3/4	9.918	1932	196.9	1985	202.3
46		10.364	2019	205.8	2075	211.4
48		11.285	2199	224	2259	230.2
50	2	12.245	2386	243.1	2451	249.8
52		13.244	2580	262.9	2651	270.1
54	2-1/8	14.282	2783	283.6		
56		15.360	2993	305		

Update  
2015/05



Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs		
			Rope grade		
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	1960	2160
8	5/16	0.21	0.1	6.9	7.1
9		0.27	0.12	8.7	8.9
10		0.33	0.15	10.7	11
11	7/16	0.4	0.18	13	13.3
12		0.47	0.22	15.4	15.9
12.7	1/2	0.53	0.24	17.3	17.8
13		0.56	0.25	18.1	18.6
14		0.65	0.29	21	21.6
15		0.74	0.34	24.1	24.8
16	5/8	0.84	0.38	27.5	28.2
17		0.95	0.43	31	31.8
18		1.07	0.48	34.8	35.7
19	3/4	1.19	0.54	38.7	39.8
20		1.32	0.6	42.9	44.1
21		1.45	0.66	47.3	48.6
22		1.59	0.72	51.9	53.3
22.4		1.65	0.75	53.8	55.3
23		1.74	0.79	56.7	58.3
24		1.9	0.86	61.8	63.5
25		2.06	0.93	67	68.9
25.4	1	2.12	0.96	69.2	71.1
26		2.22	1.01	72.5	74.5
27		2.4	1.09	78.2	80.3
28		2.58	1.17	84.1	86.4
28.6	1-1/8	2.69	1.22	87.7	90.1
29		2.77	1.26	90.2	92.7
30		2.96	1.34	96.5	99.2
31		3.16	1.44	103.1	105.9
32	1-1/4	3.37	1.53	109.8	112.8
33		3.58	1.63	116.8	120
34		3.8	1.73	124	127.4
35	1-3/8	4.03	1.83	131.4	135
36		4.27	1.94	139	142.8
38	1-1/2	4.75	2.16	154.9	159.1
40		5.27	2.39	171.6	176.3
41		5.53	2.51	180.3	185.2
42		5.81	2.63	189.2	194.4
43		6.09	2.76	198.3	203.8
44		6.37	2.89	207.7	213.3
45	1-3/4	6.66	3.02	217.2	223.2
46		6.96	3.16	227	233.2
48		7.58	3.44	247.1	253.9
50	2	8.23	3.73	268.2	275.5
52		8.9	4.04	290	298
54	2-1/8	9.6	4.35	312.8	
56		10.32	4.68	336.4	


\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

1) The values are indicative only. Authoritative figures remain the metric ones!

The rope is fully lubricated. The finish available is either bright or galvanized. • Average fill factor 0.738 • Lay type: Lang Lay • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309; RCN=23-2 • Further details: [www.verope.com/en/RCN](http://www.verope.com/en/RCN)

# verotop S

Provides excellent breaking strength and very good resistance to rotation.



Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
13		0.847	166.0	16.9	172.8	17.6
14		0.982	192.5	19.6	200.4	20.4
15		1.127	221.0	22.5	230.1	23.4
16	5/8	1.283	251.4	25.6	261.8	26.7
17		1.448	283.8	28.9	295.5	30.1
18		1.623	318.2	32.4	331.3	33.8
19	3/4	1.809	354.5	36.1	369.2	37.6
20		2.004	392.8	40	409.0	41.7
21		2.210	433.1	44.1	451.0	46
22		2.425	475.3	48.4	494.9	50.4
22.4		2.514	492.8	50.2	513.1	52.3
23		2.651	519.5	52.9	541.0	55.1
24		2.886	565.7	57.6	589.0	60
25		3.132	613.8	62.5	639.1	65.1
25.4	1	3.233	633.6	64.6	659.7	67.2
26		3.387	663.9	67.7	691.3	70.4
27		3.653	715.9	73	745.5	76
28		3.928	770.0	78.5	801.7	81.7
28.6	1-1/8	4.099	803.3	81.9	836.5	85.2
29		4.214	825.9	84.2	860.0	87.6
30		4.510	883.9	90.1	920.4	93.8
31		4.815	943.8	96.2	982.7	100.1
32	1-1/4	5.131	1005.7	102.5	1047	106.7
33		5.457	1069	109	1114	113.5
34		5.792	1135	115.7	1182	120.5
35	1-3/8	6.138	1203	122.6	1253	127.7
36		6.494	1273	129.7	1325	135
38	1-1/2	7.235	1418	144.5	1477	150.5
40		8.017	1571	160.1	1636	166.7

\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.



Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs		
			1960	2160	
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	1960	2160
13		0.57	0.26	18.7	19.4
14		0.66	0.3	21.6	22.5
15		0.76	0.34	24.8	25.9
16	5/8	0.86	0.39	28.3	29.4
17		0.97	0.44	31.9	33.2
18		1.09	0.49	35.8	37.2
19	3/4	1.22	0.55	39.8	41.5
20		1.35	0.61	44.2	46
21		1.48	0.67	48.7	50.7
22		1.63	0.74	53.4	55.6
22.4		1.69	0.77	55.4	57.7
23		1.78	0.81	58.4	60.8
24		1.94	0.88	63.6	66.2
25		2.1	0.95	69	71.8
25.4	1	2.17	0.99	71.2	74.2
26		2.28	1.03	74.6	77.7
27		2.45	1.11	80.5	83.8
28		2.64	1.2	86.5	90.1
28.6	1-1/8	2.75	1.25	90.3	94
29		2.83	1.28	92.8	96.7
30		3.03	1.37	99.3	103.4
31		3.24	1.47	106.1	110.5
32	1-1/4	3.45	1.56	113	117.7
33		3.67	1.66	120.2	125.2
34		3.89	1.77	127.6	132.9
35	1-3/8	4.12	1.87	135.2	140.8
36		4.36	1.98	143.1	149
38	1-1/2	4.86	2.21	159.4	166
40		5.39	2.44	176.6	183.9

1) The values are indicative only. Authoritative figures remain the metric ones!

The rope is fully lubricated. The finish available is either bright or galvanized. • Average fill factor 0.755 • Lay type: Lang Lay • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309: RCN=23-2 • Further details: www.verope.com/en/RCN

# verotop E

Combines high breaking strength and good rotation resistance with remarkable efficiency.



Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
8	5/16	0.305	55.2	5.6	60.2	6.1
9		0.387	69.8	7.1	76.2	7.8
10		0.477	86.2	8.8	94.1	9.6
11	7/16	0.577	104.3	10.6	113.9	11.6
12		0.687	124.1	12.6	135.5	13.8
13		0.806	145.7	14.8	159.1	16.2
14		0.935	169.0	17.2	184.5	18.8
15		1.074	194.0	19.8	211.8	21.6
16	5/8	1.222	220.7	22.5	241.0	24.6
18		1.546	279.3	28.5	305.0	31.1
19	3/4	1.723	311.2	31.7	339.8	34.6
20		1.909	344.8	35.1	376.5	38.4
22		2.310	417.2	42.5	455.6	46.4
23		2.524	456.0	46.5	497.9	50.7
24		2.749	496.5	50.6	542.1	55.2
25		2.983	538.8	54.9	588.3	59.9
26		3.226	582.7	59.4	636.3	64.8
27		3.479	628.4	64	686.2	69.9
28		3.741	675.8	68.9	737.9	75.2
29		4.013	725.0	73.9	791.6	80.7
30		4.295	775.8	79.1	847.1	86.3
32	1-1/4	4.887	882.7	90	963.8	98.2
34		5.517	983.8	100.3	1077	109.8
35	1-3/8	5.846	1043	106.2	1142	116.3
36		6.185	1103	112.4	1208	123.1
38	1-1/2	6.891	1229	125.2	1346	137.1
40		7.635	1362	138.8	1491	151.9

\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.

Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs		
			Rope grade		
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	1960	2160
8	5/16	0.21	0.09	6.2	6.8
9		0.26	0.12	7.8	8.6
10		0.32	0.15	9.7	10.6
11	7/16	0.39	0.18	11.7	12.8
12		0.46	0.21	14	15.2
13		0.54	0.25	16.4	17.9
14		0.63	0.29	19	20.7
15		0.72	0.33	21.8	23.8
16	5/8	0.82	0.37	24.8	27.1
18		1.04	0.47	31.4	34.3
19	3/4	1.16	0.53	35	38.2
20		1.28	0.58	38.8	42.3
22		1.55	0.7	46.9	51.2
23		1.7	0.77	51.3	56
24		1.85	0.84	55.8	60.9
25		2	0.91	60.6	66.1
26		2.17	0.98	65.5	71.5
27		2.34	1.06	70.6	77.1
28		2.51	1.14	76	82.9
29		2.7	1.22	81.5	89
30		2.89	1.31	87.2	95.2
32	1-1/4	3.28	1.49	99.2	108.3
34		3.71	1.68	110.6	121.1
35	1-3/8	3.93	1.78	117.2	128.3
36		4.16	1.89	124	135.8
38	1-1/2	4.63	2.1	138.1	151.3
40		5.13	2.33	153.1	167.6

1) The values are indicative only. Authoritative figures remain the metric ones!

The rope is fully lubricated. The finish available is either bright or galvanized. • Average fill factor 0.700 • Lay type: Lang Lay • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309; RCN=23-2 • Further details: [www.verope.com/en/RCN](http://www.verope.com/en/RCN)

# verostar 8


Achieves best service life in reeving systems with single layer drums.

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1770		1960	
mm*	Inch	kg/m	kN	t	kN	t
8	5/16	0.276	47.9	4.9	53.0	5.4
9		0.349	60.6	6.2	67.1	6.8
10		0.431	74.8	7.6	82.8	8.4
11	7/16	0.522	90.5	9.2	100.2	10.2
12		0.621	107.7	11	119.3	12.2
12.7	1/2	0.695	120.6	12.3	133.6	13.6
13		0.729	126.4	12.9	140.0	14.3
14		0.845	146.6	14.9	162.3	16.5
15		0.970	168.3	17.1	186.3	19
16	5/8	1.104	191.5	19.5	212.0	21.6
17		1.246	216.2	22	239.4	24.4
18		1.397	242.3	24.7	268.3	27.3
19	3/4	1.557	270.0	27.5	299.0	30.5
20		1.725	299.2	30.5	331.3	33.8
21		1.902	329.8	33.6	365.2	37.2
22		2.087	362.0	36.9	400.9	40.8
22.4		2.164	375.3	38.2	415.6	42.3
23		2.281	395.7	40.3	438.1	44.6
24		2.484	430.8	43.9	477.1	48.6
25		2.695	467.5	47.6	517.6	52.7
25.4	1	2.782	482.5	49.2	534.3	54.4
26		2.915	505.6	51.5	559.9	57.1
27		3.143	545.2	55.6	603.8	61.5
28		3.380	586.4	59.8	649.3	66.2
28.6	1-1/8	3.527	611.8	62.3	677.4	69
29		3.626	629.0	64.1	696.5	71
30		3.881	673.1	68.6	745.4	76
31		4.144	718.8	73.2	795.9	81.1
32	1-1/4	4.415	765.9	78	848.1	86.4
33		4.696	814.5	83	901.9	91.9
34		4.984	864.6	88.1	957.4	97.6
35	1-3/8	5.282	916.2	93.4	1015	103.4
36		5.588	969.3	98.8	1073	109.4
38	1-1/2	6.226	1080	110.1	1196	121.9
40		6.899	1197	121.9	1325	135
41.3	1-5/8	7.355	1276	130	1413	144
42		7.606	1319	134.4	1461	148.9
44		8.348	1448	147.6	1603	163.4
45	1-3/4	8.731	1515	154.3	1677	170.9
46		9.124	1583	161.3	1753	178.6
47.5	1-7/8	9.729	1688	172	1869	190.4
48		9.934	1723	175.6	1908	194.4
50	2	10.780	1870	190.5	2071	211
52		11.659	2022	206.1	2239	228.2
54	2-1/8	12.573	2181	222.2	2415	246.1
56		13.522	2346	239	2597	264.7
58		14.505	2516	256.4	2786	283.9
60	2-3/8	15.523	2693	274.4	2982	303.8

\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.

Update  
2015/05




Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs	
			Rope grade	
			1770	1960
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	
8	5/16	0.19	0.08	5.4
9		0.23	0.11	6.8
10		0.29	0.13	8.4
11	7/16	0.35	0.16	10.2
12		0.42	0.19	12.1
12.7	1/2	0.47	0.21	13.6
13		0.49	0.22	14.2
14		0.57	0.26	16.5
15		0.65	0.3	18.9
16	5/8	0.74	0.34	21.5
17		0.84	0.38	24.3
18		0.94	0.43	27.2
19	3/4	1.05	0.47	30.3
20		1.16	0.53	33.6
21		1.28	0.58	37.1
22		1.4	0.64	40.7
22.4		1.45	0.66	42.2
23		1.53	0.7	44.5
24		1.67	0.76	48.4
25		1.81	0.82	52.5
25.4	1	1.87	0.85	54.2
26		1.96	0.89	56.8
27		2.11	0.96	61.3
28		2.27	1.03	65.9
28.6	1-1/8	2.37	1.08	68.8
29		2.44	1.11	70.7
30		2.61	1.18	75.7
31		2.78	1.26	80.8
32	1-1/4	2.97	1.35	86.1
33		3.16	1.43	91.5
34		3.35	1.52	97.2
35	1-3/8	3.55	1.61	103
36		3.76	1.7	109
38	1-1/2	4.18	1.9	121.4
40		4.64	2.1	134.5
41.3	1-5/8	4.94	2.24	143.4
42		5.11	2.32	148.3
44		5.61	2.55	162.8
45	1-3/4	5.87	2.66	170.2
46		6.13	2.78	177.9
47.5	1-7/8	6.54	2.97	189.7
48		6.68	3.03	193.7
50	2	7.24	3.29	210.2
52		7.83	3.55	227.3
54	2-1/8	8.45	3.83	245.1
56		9.09	4.12	263.6
58		9.75	4.42	282.8
60	2-3/8	10.43	4.73	302.6

1) The values are indicative only. Authoritative figures remain the metric ones!

The rope is fully lubricated. The finish available as standard is bright, galvanized finish on request. • Average fill factor 0.610 • Ordinary or Lang Lay available • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309 • Nominal rope diameter till 42mm RCN=09 • Nominal rope diameter 43mm to 48mm RCN=11 • Further details: www.verope.com/en/RCN Nominal rope diameter above 48mm RCN=13

# veropro 8

Rope with very high structural stability,  
achieves excellent bending fatigue results.



Nominal rope diameter		Approx mass	Minimum breaking force					
			Rope grade					
			1770		1960		2160	
mm*	Inch	kg/m	kN	t	kN	t	kN	t
8	5/16	0.288	52.1	5.3	57.7	5.9	60.6	6.2
9		0.364	66.0	6.7	73.0	7.4	76.7	7.8
10		0.450	81.5	8.3	90.1	9.2	94.7	9.6
11	7/16	0.544	98.6	10	109.1	11.1	114.6	11.7
12		0.648	117.3	12	129.8	13.2	136.3	13.9
12.7	1/2	0.726	131.4	13.4	145.4	14.8	152.7	15.6
13		0.760	137.7	14	152.3	15.5	160.0	16.3
14		0.882	159.7	16.3	176.7	18	185.6	18.9
15		1.012	183.3	18.7	202.8	20.7	213.0	21.7
16	5/8	1.152	208.6	21.3	230.7	23.5	242.4	24.7
17		1.300	235.5	24	260.5	26.5	273.6	27.9
18		1.457	264.0	26.9	292.0	29.8	306.8	31.3
19	3/4	1.624	294.2	30	325.4	33.2	341.8	34.8
20		1.799	325.9	33.2	360.5	36.7	378.7	38.6
21		1.984	359.3	36.6	397.5	40.5	417.5	42.5
22		2.177	394.4	40.2	436.2	44.5	458.3	46.7
22.4		2.257	408.9	41.7	452.2	46.1	475.1	48.4
23		2.380	431.0	43.9	476.8	48.6	500.9	51
24		2.591	469.3	47.8	519.1	52.9	545.4	55.6
25		2.812	509.3	51.9	563.3	57.4	591.8	60.3
25.4	1	2.902	525.7	53.6	581.5	59.3	610.8	62.2
26		3.041	550.8	56.1	609.3	62.1	640.0	65.2
27		3.279	594.0	60.5	657.0	67	690.2	70.3
28		3.527	638.8	65.1	706.6	72	742.3	75.6
28.6	1-1/8	3.680	666.5	67.9	737.2	75.1	774.5	78.9
29		3.783	685.3	69.8	758.0	77.2	796.3	81.1
30		4.049	733.4	74.7	811.1	82.7	852.1	86.8
31		4.323	783.1	79.8	866.1	88.3	909.9	92.7
32	1-1/4	4.606	834.4	85	922.9	94	969.5	98.8
33		4.899	887.4	90.4	981.5	100	1031	105.1
34		5.200	941.9	96	1042	106.2	1095	111.5
35	1-3/8	5.511	998.2	101.7	1104	112.5	1160	118.2
36		5.830	1056	107.6	1168	119	1227	125
38	1-1/2	6.496	1177	119.9	1301	132.6	1367	139.3
40		7.198	1304	132.9	1442	146.9	1515	154.4
41.3	1-5/8	7.673	1390	141.6	1537	156.7	1615	164.6
42		7.935	1437	146.5	1590	162	1670	170.2
44		8.709	1578	160.7	1745	177.8	1833	186.8
45	1-3/4	9.109	1650	168.1	1825	186	1917	195.4
46		9.519	1724	175.7	1907	194.3	2003	204.2
47.5	1-7/8	10.150	1838	187.3	2034	207.2	2136	217.7
48		10.364	1877	191.3	2077	211.6	2181	222.3
50	2	11.246	2037	207.6	2253	229.6	2367	241.2
52		12.164	2203	224.5	2437	248.3	2560	260.9
54	2-1/8	13.117	2376	242.1	2628	267.8	2761	281.3
56		14.107	2555	260.4	2826	288		
58		15.133	2741	279.3	3032	309		
60	2-3/8	16.194	2933	298.9	3245	330.6		

Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force					
			Rope grade					
			1770		1960		2160	
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	lb/ft <sup>1</sup>
8	5/16	0.19	0.09	5.9	6.5	6.8		
9		0.24	0.11	7.4	8.2	8.6		
10		0.3	0.14	9.2	10.1	10.6		
11	7/16	0.37	0.17	11.1	12.3	12.9		
12		0.44	0.2	13.2	14.6	15.3		
12.7	1/2	0.49	0.22	14.8	16.3	17.2		
13		0.51	0.23	15.5	17.1	18		
14		0.59	0.27	18	19.9	20.9		
15		0.68	0.31	20.6	22.8	23.9		
16	5/8	0.77	0.35	23.4	25.9	27.2		
17		0.87	0.4	26.5	29.3	30.8		
18		0.98	0.44	29.7	32.8	34.5		
19	3/4	1.09	0.5	33.1	36.6	38.4		
20		1.21	0.55	36.6	40.5	42.6		
21		1.33	0.6	40.4	44.7	46.9		
22		1.46	0.66	44.3	49	51.5		
22.4		1.52	0.69	46	50.8	53.4		
23		1.6	0.73	48.4	53.6	56.3		
24		1.74	0.79	52.8	58.4	61.3		
25		1.89	0.86	57.2	63.3	66.5		
25.4	1	1.95	0.88	59.1	65.4	68.7		
26		2.04	0.93	61.9	68.5	71.9		
27		2.2	1	66.8	73.9	77.6		
28		2.37	1.08	71.8	79.4	83.4		
28.6	1-1/8	2.47	1.12	74.9	82.9	87		
29		2.54	1.15	77	85.2	89.5		
30		2.72	1.23	82.4	91.2	95.8		
31		2.9	1.32	88	97.4	102.3		
32	1-1/4	3.1	1.4	93.8	103.7	109		
33		3.29	1.49	99.7	110.3	115.9		
34		3.49	1.59	105.9	117.1	123		
35	1-3/8	3.7	1.68	112.2	124.1	130.4		
36		3.92	1.78	118.7	131.3	137.9		
38	1-1/2	4.36	1.98	132.3	146.3	153.7		
40		4.84	2.19	146.5	162.1	170.3		
41.3	1-5/8	5.16	2.34	156.2	172.8	181.5		
42		5.33	2.42	161.6	178.7	187.7		
44		5.85	2.66	177.3	196.1	206		
45	1-3/4	6.12	2.78	185.5	205.1	215.5		
46		6.4	2.9	193.8	214.4	225.2		
47.5	1-7/8	6.82	3.09	206.6	228.6	240.1		
48		6.96	3.16	211	233.4	245.2		
50	2	7.56	3.43	229	253.3	266.1		
52		8.17	3.71	247.7	273.9	287.8		
54	2-1/8	8.81	4	267.1	295.4	310.3		
56		9.48	4.3	287.2	317.7			
58		10.17	4.61	308.1	340.8			
60	2-3/8	10.88	4.94	329.7	364.7			

\* Standard tolerance: +2% to +4%, other tolerances possible upon request.  
Other and special rope diameters are available upon request.

1) The values are indicative only. Authoritative figures remain the metric ones!

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.

The rope is fully lubricated. The finish available as standard is galvanized, bright finish on request. • Average fill factor 0.666 • Ordinary or Lang Lay available • Rope Category Number (RCN) to determine the number of visible broken outer wires, signalling discard of rope acc. ISO 4309 • Nominal rope diameter till 42 mm RCN=09 • Nominal rope diameter 43mm to 48mm RCN=13 • Further details: www.verope.com/en/RCN

# veropro 8 RS



Provides excellent resistance to abrasion  
and has a very high breaking strength.

Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
12		0.666	134.4	13.7	144.7	14.7
12.7	1/2	0.746	150.5	15.3	162.1	16.5
13		0.782	157.7	16.1	169.9	17.3
14		0.907	182.9	18.6	197.0	20.1
15		1.041	210.0	21.4	226.1	23
16	5/8	1.184	238.9	24.3	257.3	26.2
17		1.337	269.7	27.5	290.5	29.6
18		1.499	302.4	30.8	325.6	33.2
19	3/4	1.670	336.9	34.3	362.8	37
20		1.851	373.3	38	402.0	41
21		2.040	411.5	41.9	443.2	45.2
22		2.239	451.7	46	486.5	49.6
22.4		2.322	468.2	47.7	504.3	51.4
23		2.448	493.7	50.3	531.7	54.2
24		2.665	537.5	54.8	578.9	59
25		2.892	583.3	59.4	628.2	64
25.4	1	2.985	602.1	61.4	648.4	66.1
26		3.128	630.9	64.3	679.4	69.2
27		3.373	680.3	69.3	732.7	74.7
28		3.627	731.6	74.6	788.0	80.3
28.6	1-1/8	3.785	763.3	77.8	822.1	83.8
29		3.891	784.8	80	845.3	86.1
30		4.164	839.9	85.6	904.6	92.2
31		4.446	896.8	91.4	965.9	98.4
32	1-1/4	4.738	955.6	97.4	1029	104.9
33		5.039	1016	103.6	1095	111.5
34		5.349	1079	109.9	1162	118.4
35	1-3/8	5.668	1143	116.5	1231	125.5
36		5.996	1209	123.2	1303	132.7
38	1-1/2	6.681	1348	137.3	1451	147.9
40		7.403	1493	152.2	1608	163.9
41.3	1-5/8	7.892	1592	162.2	1714	174.7
42		8.162	1646	167.7	1773	180.7
44		8.957	1807	184.1	1946	198.3
45	1-3/4	9.369	1890	192.6	2035	207.4
46		9.790	1975	201.2	2127	216.7
47.5	1-7/8	10.439	2106	214.6	2268	231.1
48		10.660	2150	219.1	2316	236

\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.




Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs		
			Rope grade		
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	1960	2160
12		0.45	0.2	15.1	16.3
12.7	1/2	0.5	0.23	16.9	18.2
13		0.53	0.24	17.7	19.1
14		0.61	0.28	20.6	22.1
15		0.7	0.32	23.6	25.4
16	5/8	0.8	0.36	26.9	28.9
17		0.9	0.41	30.3	32.6
18		1.01	0.46	34	36.6
19	3/4	1.12	0.51	37.9	40.8
20		1.24	0.56	42	45.2
21		1.37	0.62	46.3	49.8
22		1.5	0.68	50.8	54.7
22.4		1.56	0.71	52.6	56.7
23		1.64	0.75	55.5	59.8
24		1.79	0.81	60.4	65.1
25		1.94	0.88	65.6	70.6
25.4	1	2.01	0.91	67.7	72.9
26		2.1	0.95	70.9	76.4
27		2.27	1.03	76.5	82.4
28		2.44	1.11	82.2	88.6
28.6	1-1/8	2.54	1.15	85.8	92.4
29		2.61	1.19	88.2	95
30		2.8	1.27	94.4	101.7
31		2.99	1.36	100.8	108.6
32	1-1/4	3.18	1.44	107.4	115.7
33		3.39	1.54	114.2	123
34		3.59	1.63	121.3	130.6
35	1-3/8	3.81	1.73	128.5	138.4
36		4.03	1.83	135.9	146.4
38	1-1/2	4.49	2.04	151.5	163.1
40		4.97	2.26	167.8	180.8
41.3	1-5/8	5.3	2.41	178.9	192.7
42		5.48	2.49	185	199.3
44		6.02	2.73	203.1	218.7
45	1-3/4	6.3	2.86	212.4	228.8
46		6.58	2.98	222	239
47.5	1-7/8	7.01	3.18	236.7	254.9
48		7.16	3.25	241.7	260.3

1) The values are indicative only. Authoritative figures remain the metric ones!

The rope is fully lubricated. The finish available as standard is galvanized, bright finish on request. • Average fill factor 0.685 • Ordinary or Lang Lay available • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309 • Nominal rope diameter till 42mm RCN=09 • Nominal rope diameter 43mm to 48mm RCN=11  
Nominal rope diameter above 48mm RCN=13 • Further details: www.verope.com/en/RCN

# veropower 8

Provides the highest breaking strength of all non-rotation resistant ropes and offers superior resistance to drum crushing.



Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
12		0.717	147.4	15	158.8	16.2
12.7	1/2	0.803	165.1	16.8	177.9	18.1
13		0.842	173.0	17.6	186.4	19
14		0.976	200.6	20.4	216.2	22
15		1.121	230.3	23.5	248.2	25.3
16	5/8	1.275	262.0	26.7	282.3	28.8
17		1.440	295.8	30.1	318.7	32.5
18		1.614	331.6	33.8	357.3	36.4
19	3/4	1.798	369.5	37.6	398.1	40.6
20		1.992	409.4	41.7	441.2	45
21		2.197	451.3	46	486.4	49.6
22		2.411	495.3	50.5	533.8	54.4
22.4		2.499	513.5	52.3	553.4	56.4
23		2.635	541.4	55.2	583.4	59.5
24		2.869	589.5	60.1	635.3	64.7
25		3.113	639.6	65.2	689.3	70.2
25.4	1	3.214	660.3	67.3	711.5	72.5
26		3.367	691.8	70.5	745.6	76
27		3.631	746.1	76	804.0	81.9
28		3.905	802.4	81.8	864.7	88.1
28.6	1-1/8	4.074	837.1	85.3	902.1	91.9
29		4.189	860.7	87.7	927.5	94.5
30		4.483	921.1	93.9	992.6	101.1
31		4.787	983.5	100.2	1060	108
32	1-1/4	5.101	1048	106.8	1129	115.1
33		5.424	1115	113.6	1201	122.4
34		5.758	1183	120.6	1275	129.9
35	1-3/8	6.102	1254	127.8	1351	137.7
36		6.455	1326	135.2	1429	145.7
38	1-1/2	7.193	1478	150.6	1593	162.3
40		7.970	1637	166.9	1765	179.8
41.3	1-5/8	8.496	1746	177.9	1881	191.7
42		8.787	1805	184	1946	198.2
44		9.643	1981	201.9	2135	217.6
45	1-3/4	10.09	2072	211.2	2233	227.6
46		10.54	2166	220.7	2334	237.8
47.5	1-7/8	11.24	2309	235.3	2488	253.6
48		11.48	2358	240.3	2541	258.9

Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs		
			Rope grade		
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	1960	2160
12		0.48	0.22	16.6	17.9
12.7	1/2	0.54	0.24	18.6	20
13		0.57	0.26	19.4	21
14		0.66	0.3	22.5	24.3
15		0.75	0.34	25.9	27.9
16	5/8	0.86	0.39	29.4	31.7
17		0.97	0.44	33.2	35.8
18		1.08	0.49	37.3	40.2
19	3/4	1.21	0.55	41.5	44.8
20		1.34	0.61	46	49.6
21		1.48	0.67	50.7	54.7
22		1.62	0.74	55.7	60
22.4		1.68	0.76	57.7	62.2
23		1.77	0.8	60.9	65.6
24		1.93	0.87	66.3	71.4
25		2.09	0.95	71.9	77.5
25.4	1	2.16	0.98	74.2	80
26		2.26	1.03	77.8	83.8
27		2.44	1.11	83.9	90.4
28		2.62	1.19	90.2	97.2
28.6	1-1/8	2.74	1.24	94.1	101.4
29		2.81	1.28	96.7	104.3
30		3.01	1.37	103.5	111.6
31		3.22	1.46	110.5	119.1
32	1-1/4	3.43	1.56	117.8	126.9
33		3.64	1.65	125.3	135
34		3.87	1.76	133	143.3
35	1-3/8	4.1	1.86	140.9	151.9
36		4.34	1.97	149.1	160.7
38	1-1/2	4.83	2.19	166.1	179
40		5.36	2.43	184.1	198.3
41.3	1-5/8	5.71	2.59	196.2	211.4
42		5.9	2.68	202.9	218.7
44		6.48	2.94	222.7	240
45	1-3/4	6.78	3.08	232.9	251
46		7.08	3.21	243.4	262.3
47.5	1-7/8	7.55	3.43	259.5	279.7
48		7.71	3.5	265	285.6

\* Standard tolerance: +2% to +4%, other tolerances possible upon request.  
Other and special rope diameters are available upon request.


1) The values are indicative only. Authoritative figures remain the metric ones!

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.

The rope is fully lubricated. The finish available as standard is galvanized, bright finish on request. • Average fill factor 0.747 • Lay type: Ordinary Lay • Rope Category Number (RCN) to determine the number of visible broken outer wires, signaling discard of rope acc. ISO 4309 • Nominal rope diameter till 40mm RCN=09 • Nominal rope diameter 41mm to 46mm RCN=13 • Further details: www.verope.com/en/RCN

# veropro 10

Extremely flexible rope with very high breaking strength, achieves excellent bending fatigue results.



Update  
2015/05

Nominal rope diameter		Approx mass	Minimum breaking force			
			Rope grade			
			1960		2160	
mm*	Inch	kg/m	kN	t	kN	t
30		4.152	828.0	84.4	891.6	90.9
32	1-1/4	4.724	942.1	96	1014.4	103.4
34		5.333	1063.5	108.4	1145.2	116.7
36		5.979	1192.3	121.5	1283.9	130.8
38	1-1/2	6.662	1328.4	135.4	1430.5	145.8
40		7.381	1472.0	150	1585.1	161.5
42		8.138	1622.8	165.4	1747.5	178.1
44		8.931	1781.1	181.5	1917.9	195.4
46		9.762	1946.7	198.4	2096.3	213.6
48		10.629	2119.6	216	2282.5	232.6
50	2	11.533	2299.9	234.4	2476.7	252.4
52		12.474	2487.6	253.5	2678.8	273
54	2-1/8	13.452	2682.6	273.4	2888.8	294.4
56		14.467	2885.0	294	3106.8	316.6
58		15.519	3094.8	315.4	3332.6	339.6
60	2-3/8	16.608	3311.9	337.5	3566.4	363.4
62		17.733	3536.4	360.4	3808.1	388.1
64	2-1/2	18.896	3768.2	384	4057.8	413.5
66	2-5/8	20.095	4007.4	408.4	4315.4	439.7
68		21.332	4254.0	433.5	4580.9	466.8
70	2-3/4	22.605	4507.9	459.4	4854.3	494.7

\* Standard tolerance: +2% to +4%, other tolerances possible upon agreement.  
Other and special rope diameters are available upon request.

Errors and omissions excepted! The cross-section shows a typical rope diameter and can vary within the range.  
Subject to modifications, this may change the specifications. Relevant is our website.

Nominal rope diameter		Approx mass	Minimum breaking force tons <sup>1</sup> of 2000 lbs		
			1960	2160	
mm*	Inch	lb/ft <sup>1</sup>	kg/ft <sup>1</sup>	1960	2160
30		2.79	1.27	93.1	100.2
32	1-1/4	3.17	1.44	105.9	114
34		3.58	1.63	119.5	128.7
36		4.02	1.82	134	144.3
38	1-1/2	4.48	2.03	149.3	160.8
40		4.96	2.25	165.4	178.2
42		5.47	2.48	182.4	196.4
44		6	2.72	200.2	215.6
46		6.56	2.98	218.8	235.6
48		7.14	3.24	238.2	256.6
50	2	7.75	3.52	258.5	278.4
52		8.38	3.8	279.6	301.1
54	2-1/8	9.04	4.1	301.5	324.7
56		9.72	4.41	324.3	349.2
58		10.43	4.73	347.9	374.6
60	2-3/8	11.16	5.06	372.3	400.9
62		11.92	5.41	397.5	428
64	2-1/2	12.7	5.76	423.5	456.1
66	2-5/8	13.5	6.13	450.4	485
68		14.33	6.5	478.1	514.9
70	2-3/4	15.19	6.89	506.7	545.6

1) The values are indicative only. Authoritative figures remain the metric ones!

The rope is fully lubricated. The finish available as standard is galvanized, bright finish on request. • Average fill factor 0.683  
Ordinary or Lang Lay available • Rope Category Number (RCN) to determine the number of visible broken outer wires,  
signaling discard of rope acc. ISO 4309: RCN=11 • Further details: [www.verope.com/en/RCN](http://www.verope.com/en/RCN)


# Worldwide service and distribution

With our stock-keeping program at the different verope service centers, we are able to bridge the distance between our modern rope production facility and joint venture partner Kiswire in both South Korea and Malaysia and our customers day to day requirements locally.

## Our service and logistics centers in

- Contwig, Germany
  - Shanghai, China
  - Singapore
  - Houston, USA
  - Resende, Brasil
  - Mumbai & New Delhi, India
- are able to turn on short notice any inquiries into action.





verope has a worldwide network of professional dealers who expertly select the correct high performance rope to suit your requirements regionally.



St. Anton's-Gasse 4a  
CH-6300 Zug / Switzerland  
Tel: + 41 (0) 41 72 80 880  
Fax: + 41 (0) 41 72 80 888

[www.verope.com](http://www.verope.com)  
[info@verope.com](mailto:info@verope.com)